

PA 620-MF

Mineral Fiber Filled Nylon 12 Laser Sintering Material

Technical Data Sheet

POWDER PROPERTIES

TEST METHOD

ALM PA 620-MF

Bulk Density	ASTM D1895	0.46 grams/CC
Average Particle Size (D50)	Laser Diffraction	55 microns
Particle Size Range (D10-D90)	Laser Diffraction	30 to 100 microns
Sintered Part Density	ASTM D792	1.20 grams/CC

THERMAL PROPERTIES

TEST METHOD

ALM PA 620-MF

Melting Point	ASTM D3418	184 Deg C
Melt Flow Rate (3min, 5.0kg, 235C)	ASTM D1238	50 grams/10min

MECHANICAL PROPERTIES

TEST METHOD

ALM PA 620-MF

Heat Deflection Temp @ 0.45 MPa	ASTM D648	184 Deg C
Heat Deflection Temp @ 1.82 MPa	ASTM D648	179 Dec C
Ultimate Tensile Strength (XY)	ASTM D638	52 MPa / 7,541 psi
Tensile Modulus (XY)	ASTM D638	5,700 MPa / 827 kpsi
Flexural Modulus (XY)	ASTM D790	4,550 MPa / 660 kpsi
Elongation at Break (XY)	ASTM D638	4%
IZOD Impact Strength (Unnotched)	ASTM D256	310 J/m
IZOD Impact Strength (Notched)	ASTM D256	37.4 J/m
Volume Resistivity (23C, 50%RH, 500V)	ASTM D257	6.7 x 10 ¹⁵ ohm-cm
Surface Resistivity (23C, 50%RH, 500V)	ASTM D257	5.2 x 10 ¹⁵ ohm
Dielectric Constant	ASTM D150	3.14

Actual part properties may vary slightly from those listed above based on processing parameters, operating conditions, and material usage. The above properties were based on virgin ALM PA 620-MF using nominal operating parameters on a 2500+ platform. Advanced Laser Materials, LLC makes no warranties of materials for any particular application, nor does it make a warranty of any type, expressed or implied, including, but not limited to, the warranties of merchantability for a particular purpose.



Advanced Laser Materials, LLC • Tel: 254-773-3080 • Fax: 254-773-3084
3115 Lucius McCelvey, Temple, TX 76504 • www.alm-llc.com